

CenturyWerks Coarse Sand

Report Prepared:

October 6, 2025

Sieve	Indiv. Wt. Retained	Cumul. Wt. Retained	Cumul. % Retained	Percent % Passing	Spec Range (% Passing)	Result
1		0	0.00	100.00	-	-
3/8"		0	0.00	100.00	-	-
#4	0	0	0.00	100.00	100	P
#8	8.2	8.2	1.64	98.36	95 to 100	P
#10		8.2	1.64	98.36	-	-
#16	36.3	44.5	8.90	91.10	70 to 100	P
#30	160.84	205.34	41.07	58.93	40 to 75	P
#40		205.34	41.07	58.93	-	-
#50	163.49	368.83	73.77	26.23	10 to 35	P
#80		368.83	73.77	26.23	-	-
#100	112.26	481.09	96.22	3.78	2 to 15	P
#200	14.55	495.64	99.13	0.87	0 to 5	P
Pan	2.19	497.83	99.57	0.43		
Total Dry Mass	500					
Gain / Loss (+/-) =	-2.17					

Sand Blend Sample complies with ASTM C144

CenturyWerks Coarse Sand

■ Indiv. Wt. Retained

