



Maintain

CenturyWerks Butterjoint Sand

Report Prepared:

October 6, 2025

Sieve	Indiv. Wt. Retained	Cumul. Wt. Retained	Cumul. % Retained	Percent % Passing	Spec Range (% Passing)	Result
1		0	0.00	100.00	-	-
3/8"		0	0.00	100.00	-	-
#4	0	0	0.00	100.00	100	P
#8	0	0	0.00	100.00	95 to 100	P
#10		0	0.00	100.00	-	-
#16	0.7	0.7	0.14	99.86	70 to 100	P
#30	100.1	100.8	20.16	79.84	40 to 75	F
#40		100.8	20.16	79.84	-	-
#50	276.46	377.26	75.45	24.55	10 to 35	P
#80		377.26	75.45	24.55	-	-
#100	114.1	491.36	98.27	1.73	2 to 15	F
#200	7	498.36	99.67	0.33	0 to 5	P
Pan	1.16	499.52	99.90	0.10		
Total Dry Mass	500					
Gain / Loss (+/-) =	-0.48					

**Sand Blend Sample does not comply with ASTM C144**



## CenturyWerks Butterjoint Sand

■ Indiv. Wt. Retained

