



Maintain

CenturyWerks Mason Sand

Report Prepared:

October 6, 2025

Sieve	Indiv. Wt. Retained	Cumul. Wt. Retained	Cumul. % Retained	Percent % Passing	Spec Range (% Passing)	Result
1		0	0.00	100.00	-	-
3/8"		0	0.00	100.00	-	-
#4	0	0	0.00	100.00	100	P
#8	2.35	2.35	0.47	99.53	95 to 100	P
#10		2.35	0.47	99.53	-	-
#16	22	24.35	4.87	95.13	70 to 100	P
#30	103.7	128.05	25.61	74.39	40 to 75	P
#40		128.05	25.61	74.39	-	-
#50	223.35	351.4	70.28	29.72	10 to 35	P
#80		351.4	70.28	29.72	-	-
#100	119.85	471.25	94.25	5.75	2 to 15	P
#200	23.55	494.8	98.96	1.04	0 to 5	P
Pan	4.05	498.85	99.77	0.23		
Total Dry Mass	500					
Gain / Loss (+/-) =	-1.15					

Sand Blend Sample complies with ASTM C144



CenturyWerks Mason Sand

■ Indiv. Wt. Retained

